Peinture Cimentol
Lionel Lassus
ZAC de la Prévôté
7 Route de Bû
78550 Houdan
France

Test Report – LEED 2009 EQ c4.2, SCAQMD rule 1113 (2007)

Sample material

Sample identification	**CIMES SATIN**
Product type	APL Flat Topcoat
Product data, according to manufacturer	Density: 1.24 g/ml at 20 °C Water content: 600 g/l** Exempt compounds***.
Date received	2 February 2012
Analytical period	February 2012.

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.2 ASTM D 2369 – 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 U_m (%)

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

([g all volatiles] - [g water] - [g exempt compounds]) / ([l material] - [l water] - [l exempt compounds])

U_m **(%):** The expanded uncertainty U_m is equal to 2 x RSD%, please see www.eurofins.dk/uncertainty.

Analytical results

	Solid content, % mass	**Water content, % mass**	**VOC less water less exempt compounds, g/l**	**VOC limit g/l**
CIMES SATIN	47	60 **	< 1	50 *

* VOC limit for "Flat Topcoats".
** Given by the client
*** Not information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Inge Bondgaard
Chemical engineer