



Peinture Cimentol
Lionel Lassus
ZAC de la Prévôté
7 Route de Bû
78550 Houdan
France

Eurofins Product Testing A/S
Smedeskovvej 38
DK-8464 Galten
Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
ProductTesting-GA@eurofins.com
www.eurofins.com/product-emissions

Date
25 June 2012

Your ref.

-

Our ref.
G16250/IB

Test Report – LEED 2009 EQ c4.2, SCAQMD rule 1113 (2007)

Sample material

Sample identification	EKSOSOL
Product type	Floor coating
Product data, according to manufacturer	Density: 1.26 g/ml at 20 °C (mixing ratio 81:19) Water content: 490 g/l** Exempt compounds***.
Date received	8 June 2012
Analytical period	June 2012.

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.2 ASTM D 2369 – 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 U _m (%)
Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as: ([g all volatiles] - [g water] - [g exempt compounds]) / ([l material] - [l water] - [l exempt compounds])				

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, please see www.eurofins.dk/uncertainty.

Analytical results

	Solid content, % mass	Water content, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
EKSOSOL /	54.1	39	88	100 *

* VOC limit for "Floor coatings".

** Given by the client

*** Not information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Inge Bondgaard
Chemical engineer