



Peinture Cimentol Lionel Lassus ZAC de la Prévôté 7 Route de Bû 78550 Houdan France Eurofins Product Testing A/S Smedeskovvej 38 DK-8464 Galten Denmark

Tel. +45 70 22 42 76
Fax +45 70 22 42 75
ProductTesting-GA@eurofins.com
www.eurofins.com/product-emissions

Date

9 August 2012

Your ref.

_

Our ref. G17064

Test Report – LEED 2009 EQ c4.2, SCAQMD rule 1113 (2007)

Sample material

- Triatoriai				
Sample identification	EKOPUR			
Product type	Flat Topcoat			
Product data, according to manufacturer	Density: 1.38 g/ml at 20 °C Water content: 614 g/l** Exempt compounds***.			
Date received	23 July 2012			
Analytical period	July to August 2012.			

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.2	Crovinantria	Total Volatiles, SCAQMD rule 304	1 g/l	10 U _m (%)
ASTM D 2369 – 10	Gravimetric			

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

([g all volatiles] - [g water] - [g exempt compounds])/([l material] - [l water] - [l exempt compounds])

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, please see www.eurofins.dk/uncertainty.

Analytical results

	Solid content, % mass	Water content, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
EKOPUR SATIN	59	45**	0	50 *

^{*} VOC limit for "Flat Topcoats".

Eurofins Product Testing A/S

Thomas Neuhaus

^{**} Given by the client

^{***} Not information about exempt compounds. Set to zero.